

**Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application.

**Listing of Claims:**

1. (Currently Amended) A method for producing a colloidal dispersion of nanoparticles of at least one conductive material in a dense fluid medium, the method comprising the steps of:

- (a) providing a reaction vessel for containing the dense fluid medium;
- (b) charging the dense fluid medium into the reaction vessel;
- (c) providing a rotatable first electrode comprising a first conductive material and terminated in a ceramic pin-array holder, the rotatable first electrode having (i) an end piece with a planar surface and (ii) an array of pins mounted in the pin-array holder and the planar surface; the first electrode immersed within the dense fluid medium;
- (d) ~~providing a ceramic pin holder on the end piece of the first electrode;~~
- (e) ~~providing multiple pins comprising a conductive material projecting from the end piece of the first electrode and mounted in the ceramic holder;~~
- (f) ~~providing a static second electrode comprising a second conductive material and having a planar surface,~~ the second electrode immersed within the dense fluid medium and being near to the first electrode;
- (eg) rotating the first electrode such that the dense medium is circulated between the first and second electrodes; and
- (fh) imposing an electric potential between the rotating first electrode and the second electrode to create electrical discharges between the pins and the planar surface of the second electrode~~a discharge zone~~, the electric potential being sufficiently high to dislocate nanoparticles of at least one of the first conductive material or the second conductive material from the respective electrode.

2. (Original) The method of claim 1 including the step of passing a gas through the discharge zone.

3. (Original) The method claim 2 wherein the gas is a reactive or inert gas.
4. (Previously Presented) The method of Claim 1 wherein the second electrode is hollow and includes at least one conduit for passage of the dense fluid medium.
5. (Original) The method of Claim 1 wherein at least one of the first conductive material or the second conductive material comprises an electrical conductor selected from the group consisting of metals, carbon or combinations thereof.
6. (Original) The method of Claim 1 wherein at least one of the first conductive material or the second conductive material comprises an electrical conductor selected from the group consisting of aluminum, antimony, bismuth, carbon, copper, gold, iron, lead, molybdenum, nickel, platinum, silver, tin, tungsten, zinc, rare earths or combinations thereof.
7. (Original) The method of Claim 1 wherein at least one of the first conductive material or the second conductive material comprises silver.
8. (Original) The method of Claim 1 wherein the nanoparticles have an average diameter of less than about 100 nm as determined by scanning electron microscopy.
9. (Original) The method of Claim 1 wherein the nanoparticles have an average diameter of less than about 50 nm as determined by scanning electron microscopy.
10. (Original) The method of Claim 1 wherein the nanoparticles have an average diameter of less than about 20 nm as determined by scanning electron microscopy.
11. (Original) The method of Claim 1 wherein the nanoparticles have an average diameter of less than about 10 nm as determined by scanning electron microscopy.
12. (Original) The method of Claim 1 wherein the first electrode rotates at a speed of up to about 5000 RPM.
13. (Original) The method of Claim 12 wherein the first electrode rotates at a speed of at least about 1000 RPM.

14. (Currently Amended) The method of Claim 1 wherein ~~the first electrode and the second electrode each comprise at least one planar surface, wherein~~ the planar surface of the first electrode is substantially parallel to the planar surface of the second electrode.

15. (Currently Amended) The method of Claim 14 wherein the pins and the planar surface of the second electrode~~substantially planar parallel surfaces~~ are separated by a gap of about 1 mm.

16. (Canceled)

17. (Original) The method of Claim 14 wherein the planar surface of the first electrode and the planar surface of the second electrode are each disk shaped.

18. (Canceled)

19. (Previously Presented) The method of Claim 1 wherein the pins are arrayed in a spiral pattern.

20. (Previously Presented) The method of Claim 1 wherein the distance between the pins and the second electrode is about 0.5 mm.

21. (Original) The method of Claim 1 wherein the electric potential is about 200 DCV.

22. (Currently Amended) The method of Claim 1 wherein the conductive material of both the first electrode and the second electrode comprises silver; and the nanoparticles have an average diameter of less than about 20 nm as determined by scanning electron microscopy.

23. (Previously Presented) The method of Claim 1 wherein the dense medium comprises water with bacteria therein and the method is carried out for a time sufficient to kill the bacteria.

24-43. (Canceled)

44. (Currently Amended) A method of producing colloidal nanoparticles comprising:

(a) providing a dense medium plasma discharge apparatus comprising:

(1) a chamber forming a reaction vessel for a dense medium;

(2) a first electrode mounted for rotation about an axis in the chamber having an end piece of conductive material with a planar surface, the first electrode terminated in a ceramic pin-array holder and a ceramic pin holder on the end piece;

(3) a plurality of pins in an array projecting from the planar surface and mounted in the ceramic pin-array holder and the planar surface of the first electrode;

(4) a second electrode mounted in the chamber and having an end piece of conductive material with a planar surface;

the planar surfaces of the end pieces of the first and second electrodes separated from each other by a gap;

(b) immersing the first and second electrodes in a dense medium;

(c) rotating the first electrode with respect to the second electrode; and

(d) imposing an electrical potential between the first electrode and the second electrode to create electrical discharges between the pins and the planar surface of the second electrode~~a discharge zone~~ to form nanoparticles between the first and second electrodes.

45. (Previously Presented) The method of Claim 44 including the step of passing a gas through the discharge zone.

46. (Previously Presented) The method of Claim 44 wherein the gas is a reactive or inert gas.

47. (Previously Presented) The method of Claim 44 wherein at least one of the first electrode conductive material or the second electrode conductive material comprises an electrical conductor selected from the group consisting of metals, carbon or combinations thereof.

48. (Previously Presented) The method of Claim 44 wherein the nanoparticles have an average diameter of less than about 100 nm as determined by scanning electron microscopy.

49. (Previously Presented) The method of Claim 44 wherein the nanoparticles have an average diameter of less than about 50 nm as determined by scanning electron microscopy.

50. (Previously Presented) The method of Claim 44 wherein the pins of the first electrode are arrayed in a spiral pattern.

51. (Previously Presented) The method of Claim 44 wherein the distance between the pins and the second electrode is about 0.5 mm.

52. (Currently Amended) A method for producing a colloidal dispersion of nanoparticles of at least one conductive material in a dense fluid medium, the method comprising the steps of:

- (a) providing a reaction vessel for containing the dense fluid medium;
- (b) charging the dense fluid medium into the reaction vessel;
- (c) providing a rotatable first electrode comprising a first conductive material and terminated in a ceramic pin holder, the rotatable first electrode having (i) an end piece with a planar surface and (ii) at least one pin made of the first conducting material mounted in the ceramic pin holder and the planar surface of the first electrode; the first electrode immersed within the dense fluid medium;
- (d) ~~providing a ceramic pin holder on the end piece of the first electrode;~~
- (e) ~~providing a static second electrode comprising a second conductive material and having a planar surface, the second electrode immersed within the dense fluid medium and being near to the first electrode, wherein the first electrode and the second electrode each comprise at least one planar surface and the planar surface of the first electrode is substantially parallel to the planar surface of the second electrode, and further wherein the first electrode comprises at least one pin made of the first conducting material, the pin projecting from the planar surface of the first electrode toward the planar surface of the second electrode and mounted in the ceramic pin holder;~~
- (ef) rotating the first electrode such that the dense medium is circulated between the first and second electrodes; and

(fg) imposing an electric potential between the rotating first electrode and the second electrode to create electrical discharges between the pins and the planar surface of the second electrode~~a discharge zone~~, the electric potential being sufficiently high to dislocate nanoparticles of at least one of the first conductive material or the second conductive material from the respective electrode.

53. (Canceled)

54. (New) The method of Claim 44 wherein the pins and the end piece of the second electrode are formed of silver and the nanoparticles are silver nanoparticles.

55. (New) The method of Claim 54 wherein the dense medium comprises water with bacteria therein and the method is carried out for a time sufficient to kill the bacteria.

56. (New) The method of Claim 54 further including the step of adding the silver nanoparticles to water contaminated with bacteria to kill the bacteria.